# **HANWHA**

# **Ethylene Vinylacetate Copolymer**

1159

**Extrusion Coating Grade** 

MELT INDEX 18.0 VA CONTENT 28.0

HANWHA EVA 1159 is manufactured by Dow autoclave high pressure process and designed for variety of extrusion coating application such as thermal film(Laminex film) and flexible film etc.. EVA 1159 is well known for its excellent processability and high quality assurance.

This product complies with U.S. FDA regulation 21 CFR 177.1350 (a)(1)

### Outstanding Properties

Very Low Heat Seal Temperature Good Drawability Good Adhesion to Various Plastic Films Good Optical Property

## Processing Conditions

Cylinder :  $160 \sim 220^{\circ}$ C Adapter/Head :  $220^{\circ}$ C

T-Dies : 220 ℃

#### Additives

No Additives

### Physical Properties

Physical Properties	Unit	Test Method	Value
Melt Index	g/10min	ASTM D1238	18.0
VA Content	wt%	HCC Method <sup>(3)</sup>	28.0
Density	g/cm³	ASTM D1505	0.949
Vicat Softening Point	$\mathbb{C}$	ASTM D1525	46
Melting Point	${\mathbb C}$	ASTM D3417	71
Tensile Strength at Break	kg/ cm <sup>2</sup>	ASTM D638	140
Elongation at Break	%	ASTM D638	920
Brittleness Temperature, F <sub>0</sub>	°C	ASTM D746	<-76
Neck-in <sup>(4)</sup>	cm	-	9.0
Allowable Coating Speed <sup>(4)</sup>	m/min	-	> 300
Heat Seal Initiation Temperature <sup>(5)</sup>	${\mathbb C}$	-	70

- 1. These are typical properties: not to be construed as specification.
- 2. The value for this property is dependent on part geometry and fabrication conditions.
- 3. Elemental Analyzer and FT-IR
- 4. Melt Temperature: 230°C, Line Speed: 100m/min., Output: 80kg/hr
- 5. Layer Structure : PET(50 μm)/LDPE(25 μm)/EVA 1159(25 μm)

Time/Pressure of Sealing: 1.0sec./2kg/cm<sup>2</sup>

