

Desmopan 9386A

900 品级系列, 酯类 / 邵氏硬度 A 85 - 89

Extrusion- and injection molding grade; very good hydrolysis and microbial resistance; good low-temperature flexibility; complies with VDE 0282-10; very large processing window; Application: Cable sheathings; Hoses, non-reinforced; Profiles

性能	测试条件	单位	标准	数值		
				drying	annealed	-
				according to specifications		
机械性能						
C 邵氏硬度 A	1s	-	DIN ISO 7619-1		86	
C 邵氏硬度 D	1s	-	DIN ISO 7619-1		34	
C 最终拉伸强度	200 mm/min	MPa	DIN 53504		38	
C 断裂应变	200 mm/min	%	DIN 53504		650	
C 10% 应变时的应力	200 mm/min	MPa	DIN 53504		1, 9	
C 50% 应变时的应力	200 mm/min	MPa	DIN 53504		5, 2	
C 100% 应变时的应力	200 mm/min	MPa	DIN 53504		6, 8	
C 300% 应变时的应力	200 mm/min	MPa	DIN 53504		10, 9	
C 压缩率	24 h; 70 ° C	%	DIN ISO 815-1, Method A		49	
C 压缩率	72 h; 23 ° C	%	DIN ISO 815-1		28	
C 压缩率	24 h; 70 ° C	%	DIN ISO 815-1, Method C		36	
C 耐磨性		mm³	ISO 4649 method A		84	
C 回弹力		%	ISO 4662		45	
C 撕裂强度	500 mm/min	kN/m	ISO 34-1		60	

热性质

C 拉伸储能模量	-20 ° C	MPa	ISO 6721-1, -4		152	
C 拉伸储能模量	20 ° C	MPa	ISO 6721-1, -4		48	
C 拉伸储能模量	60 ° C	MPa	ISO 6721-1, -4		35	

其他性能 (23 ° C)

C 密度		kg/m ³	ISO 1183-1			1110
------	--	-------------------	------------	--	--	------

建议成型工艺参数说明:

C 注塑-熔体温度		°C	-	205 - 225		
C 注塑-模具温度		°C	-			20 - 40
C 挤出-熔体温度		°C	-	180 - 210		
C Maximum drying temperature		°C	-			80

C 这些性能数据来源于 CAMPUS 塑料数据库并且依据 ISO 10350 标准的国际分类原则



Desmopan 9386A

声明

Covestro AG
Business Unit Polyurethanes
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany
www.TPU.covestro.com
www.covestro.com